


F-HHZHIGH HAZE BOPET FILM

F-HHZ is a Transparent high haze BOPET film. The Film is both side untreated or one side corona treated.

KEY FEATURES:

- One side treated special surface for adhesive coating
- High stiffness
- Excellent Machinability & Handling properties

FILM STRUCTURE



APPLICATION:

- Adhesive tape
- Extrusion coating & Lamination

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES			
THICKNESS	Internal	Micron	19	23	36	50
THICKNESS	internal	(Gauge)	76	92	144	200
YIELD	Internal	m² / kg	37.59	31.05	19.84	14.28
TILLU	internal	in² /lb	26483	21876	13978	10060
SURFACE TENSION (min) # (Corona Treated Side)	ASTM D-2578	dyne/cm	52			
COF (max) (One side to the other side)	ASTM D-1894	-	0.50	0.45	0.45	0.45
HAZE (min)	ASTM D-1003	%	8.0	10.0	12.0	14.0
TENSILE STRENGTH AT BREAK (min)	MD		1900	1900	1750	1750
	TD ASTM D-882	kg/cm²	2000	2000	2000	2000
	MD ASTM D-882	(Psi)	27000	27000	25000	25000
	TD	(F31)	28500	28500	28500	28500
ELONGATION AT BREAK (min)	MD ASTM D-882		110	115	120	125
	TD ASTM D-002	%	85	90	90	90
/20 Minute at 150°C\	MD ASTM D-1204	%	3.0			
	TD A31WID-1204	76	1.0			
W.V.T.R. (38° C & 90% RH) (typical)	ASTM F-1249	gm/m²/day	35	30	20	16
vv.v.i.i. (50 C & 50% Ki i) (typical)		(gm/100 in²/day)	2.3	2.0	1.3	1.0
OTR (23°C & 0% RH) (typical)	ASTM D-3985	cc/m²/day	90	80	70	45
OTT (25 C & O.B. T. I) (typical)	1.51.11.2 5565	(cc/100 in²/day)	5.8	5.2	4.5	2.9

[#] The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

STORAGE & HANDLING

FLEXPET[™] need to be stored in a warehouse below 35°C (95° F) and should not be exposed to direct sunlight, bright light sources or high humidity. If the material is stored in the recommended conditions, FLEXPET[™] is suitable for use within 270 days from date of shipment.

FOOD CONTACT

FLEXPETIN complies with EU and FDA regulations on plastic materials used for food grade application. Specific document and SDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

FlexFilms

Manufacturing Facilities at India | UAE | Poland | Egypt | Mexico | USA | Hungary | Russia | Nigeria ⊠ enquiry@flexfilm.com ⊕ www.flexfilm.com