


B-PNL

Superb Gloss White Voided BOPP Film

B-PNL is a high gloss & high yield white voided BOPP film, specially designed for wrap around label.



THE BIG DIFFERENTIATORS



Outstanding Opacity & Whiteness

Elegant print with appealing graphics.



Superb Gloss

Imparting subtle richness to branding.



High Yield

Low gsm & high linear mileage.



Good Stiffness

Better performance on high speed.



Good Antistatic

Good machinability.

KEY FEATURES:

- Excellent opacity & whiteness
- Superb gloss
- Excellent stiffness
- Good printability
- High yield

APPLICATIONS:

- Wrap around label

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUES	
THICKNESS		Internal	Micron	38	47
			(Gauge)	152	188
FILM DENSITY		D-1505	gm/cc	0.62	
GRAMMAGE		Internal	gm/m ²	23.6	29.1
YIELD		Internal	m ² /kg	42.4	34.4
			in ² /lb	29807	24183
TREATMENT LEVEL		D-2578	Dyne/cm	38	
TRANSMITTANCE		D-1003	%	30	25
GLOSS (at 45°)		D-2457	Unit	98	98
TENSILE STRENGTH AT BREAK	MD*	D-882	kg/cm ²	700	
	TD*			1300	
	MD*		(KPsi)	9.9	
	TD*			18.5	
ELONGATION AT BREAK	MD*	D-882	%	180	
	TD*			50	
LINEAR SHRINKAGE (max) (5 Minutes at 130°C)	MD*	D-1204	%	6.0	
	TD*			3.0	
WATER VAPOUR TRANSMISSION RATE (38°C & 90% RH)		F-1249	gm/m ² /day	6.4	5.7
			(gm/100 in ² /day)	0.41	0.37
OXYGEN TRANSMISSION RATE (23°C & 0% RH)		D-3985	cc/m ² /day	2100	1900
			(cc/100 in ² /day)	135	122

Ref no QAD UFLI S/20 – B 41/1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

STORAGE & HANDLING

FLEXOPP™ does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXOPP™ is best suitable for use within 6 months from date of dispatch.

FOOD CONTACT

FLEXOPP™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

**TDS issued on 01-04-2020. All previous versions of this grade are invalid.

FlexFilms

Manufacturing Facilities at
India | UAE | Poland | Egypt | Mexico |
USA | Hungary | Russia | Nigeria
enquiry@flexfilm.com
www.flexfilm.com