


# B-THC

## Cable Over Wrap Heat Sealable BOPP Film

B-THC is a coextruded both side heat sealable corona treated film for sumersible cable over wrap.



## THE BIG DIFFERENTIATORS



### No Joint

Leak proof for longer shelf-life & insulation resistance of cable.



### Balance COF On Both Side

High performance on cable over wrap m/c with minimal wastage.



### Optimized Seal Functionality

Improved lap seal strength.



### Fine Optics

High quality images.



### Good Antistatic

Good machinability.

## KEY FEATURES:

- Excellent machinability
- Balance slip
- Good antistatic
- Joint less

## APPLICATIONS:

- Cable over wrap

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUES
THICKNESS		Internal	Micron	25
			(Gauge)	100
FILM DENSITY		D-1505	gm/cc	0.91
GRAMMAGE		Internal	gm/m <sup>2</sup>	22.7
YIELD		Internal	m <sup>2</sup> /kg	44.0
			in <sup>2</sup> /lb	30932
TREATMENT LEVEL		D-2578	dyne/cm	38
COEFF OF FRICTION	Dynamic	D-1894	-	0.28±0.05
HAZE		D-1003	%	2.5
GLOSS (at 45°)		D-2578	Unit	85
TENSILE STRENGTH AT BREAK	MD*	D-882	kg/cm <sup>2</sup>	1200
	TD*			2500
	MD*		(KPsi)	17.0
	TD*			35.5
ELONGATION AT BREAK	MD*	D-882	%	200
	TD*			60
LINEAR SHRINKAGE (max) (5 Minutes at 130°C)	MD*	D-1204	%	6.0
	TD*			3.0
HEAT SEAL INITIATION TEMPERATURE		Internal	°C	105
HEAT SEAL STRENGTH	(Min.)	Internal	gm/25mm	300
WATER VAPOUR TRANSMISSION RATE (38°C & 90% RH)		F-1249	gm/m <sup>2</sup> /day	6.0
			(gm/100 in <sup>2</sup> /day)	0.39
OXYGEN TRANSMISSION RATE (23°C & 0% RH)		D-3985	cc/m <sup>2</sup> /day	1700
			(cc/100 in <sup>2</sup> /day)	110

Ref no QAD UFLI S/14 – B 14/3

\*MD = MACHINE DIRECTION \*TD = TRANSVERSE DIRECTION

## STORAGE & HANDLING

FLEXOPP™ does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXOPP™ is best suitable for use within 6 months from date of dispatch.

## FOOD CONTACT

FLEXOPP™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

## DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

\*\*TDS issued on 01-04-2020. All previous version of this grade are invalid.

**FlexFilms**

Manufacturing Facilities at  
India | UAE | Poland | Egypt | Mexico |  
USA | Hungary | Russia | Nigeria  
enquiry@flexfilm.com  
www.flexfilm.com