

Product Description:


B-THO is a transparent film
Both side sealable & modified with hot slip

Application:

-High speed over wrap
-CD & cassette over wrap

Key Features:

-Excellent machinability
-Both side low seal temperature
-Excellent hot slip

Film Structure


PROPERTIES	TEST METHOD (ASTM)	UNIT	TYPICAL VALUES				
			18	22	25	30	
THICKNESS	Internal	Micron	18	22	25	30	
		(Gauge)	72	88	100	120	
FILM DENSITY	D-1505	gm/cc	0.90	0.90	0.90	0.90	
GRAMMAGE	Internal	gm/m ²	16.20	19.80	22.50	27.00	
YIELD	Internal	m ² /kg	61.73	50.51	44.44	37.04	
		in ² /lb	43491	35586	31309	26096	
COEFF OF FRICTION	DYNAMIC	D-1894	-	0.30	0.30	0.30	
HAZE	D-1003	%	2.3	2.4	2.5	2.7	
GLOSS	D-2457	Unit	85	85	85	80	
TENSILE STRENGTH AT BREAK	D-882	MD*	Kg/cm ²	1300	1300	1300	1300
		TD*	Kg/cm ²	2500	2500	2500	2500
		MD*	(KPsi)	18.5	18.5	18.5	18.5
		TD*	(KPsi)	35.5	35.5	35.5	35.5
ELONGATION AT BREAK	D-882	MD	%	170	170	170	170
		TD	%	60	60	60	60
MODULUS OF ELASTICITY	D-882	MD	Kg/cm ²	18000	18000	18000	18000
		TD	Kg/cm ²	30000	30000	30000	30000
		MD	(KPsi)	255.6	255.6	255.6	255.6
		TD	(KPsi)	426.0	426.0	426.0	426.0
LINEAR SHRINKAGE (5 Minute at 130 ^o C)	D-1204	MD	%	<5.0			
		TD	%	<3.0			
HEAT SEAL INITIATION TEMPERATURE	Internal	^o C	110	110	110	110	
HEAT SEAL STRENGTH (Min.)	Internal	gm/25mm	250	250	250	250	
W.V.T.R.(38 ^o C & 90%RH)	F-1249	gm/m ² /day	6.8	6.6	6.5	6.0	
		(gm/100in ² /day)	0.44	0.43	0.42	0.38	
O.T.R. (23 ^o C & 0%RH)	D-3985	cc/m ² /day	1800	1800	1800	1700	
		(cc/100in ² /day)	116	116	116	109	

Ref no QAD UFLI S/14 - B15/2

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

STORAGE & HANDLING

FLEXOPP™ does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXOPP™ is best suitable for use up to 3 months from date of dispatch.

FOOD CONTACT

FLEXOPP™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information

****TDS issued on 11-02-2015.All previous version of this grade are invalid.**

Website: www.flexfilm.com