

F-WTU


MODIFIED PRIMER COATED WHITE OPAQUE BOPET FILM

F-WTU is a white opaque polyester film. The film is one side Modified Primer coated other side Untreated or Corona Treated.

KEY FEATURES:

- Excellent opacity & high brightness
- Excellent machinability & handling properties
- Good mechanical & thermal properties.
- One side Modified Primer coated surface provides excellent adhesion with inks & adhesive.
- Out side corona treated for improved bond with outer substrate.

FILM STRUCTURE



APPLICATION:

- Surface Printing jobs & Metallization
- Label application & Blister Packaging
- Other conversion where white backing required like lids

PROPERTIES		TEST METHOD	UNIT	TYPICAL VALUES			
THICKNESS		Internal	Micron	12	23	36	50
			(Gauge)	48	92	144	200
YIELD		Internal	m ² / kg	57.47	29.98	19.16	13.79
			in ² /lb	40490	21122	13499	9715
SURFACE TENSION (min) # (Modified Primer Coated Side) (Corona Treated Side)		ASTM D-2578	dyne/cm	52			
				52			
COF (max) (One side to the other side)		ASTM D-1894	-	0.50	0.45	0.45	0.45
OPACITY (min)		Hunter Lab	%	55	75	82	85
TENSILE STRENGTH AT BREAK (min)	MD	ASTM D-882	kg/cm ²	1700	1600	1500	1500
	TD			2000	2000	2000	2000
	MD		(Psi)	24200	22700	21300	21300
	TD			28500	28500	28500	28500
ELONGATION AT BREAK (min)	MD	ASTM D-882	%	110	115	120	125
	TD			80	80	85	85
LINEAR SHRINKAGE (max) (30 Minute at 150°C)	MD	ASTM D-1204	%	2.5			
	TD			0.8			
W.V.T.R. (38°C & 90% RH) (typical)		ASTM F-1249	gm/m ² /day	45	25	15	12
			(gm/100 in ² /day)	2.9	1.6	1.0	0.8
OTR (23°C & 0% RH) (typical)		ASTM D-3985	cc/m ² /day	160	75	45	35
			(cc/100 in ² /day)	10.3	4.8	2.9	2.2

The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

STORAGE & HANDLING

FLEXPET™ need to be stored in a warehouse below 35°C (95° F) and should not be exposed to direct sunlight, bright light sources or high humidity. If the material is stored in the recommended conditions, FLEXPET™ is suitable for use within 270 days from date of shipment.

FOOD CONTACT

FLEXPET™ complies with EU and FDA regulations on plastic materials used for food grade application. Specific document and SDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.