


B-TNL

Non Heat Sealable BOPP Film For Wrap Around Label

B-TNL is a superb gloss non heat sealable film with one side corona treatment for label applications.



THE BIG DIFFERENTIATORS



Superb Gloss

Imparting subtle richness to branding.



Good Printability

Excellent half-tone dot transfer.



Good Stiffness

Better performance on high speed.



Better Optics

Finer print images.



Good Antistatic

Good machinability.

KEY FEATURES:

- Excellent gloss & transparency
- Good printability
- Controlled slip & Antistatic
- Good dimensional stability

APPLICATIONS:

- Wrap around label

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUES								
THICKNESS		Internal	Micron	15	18	20	25	30	40	45	48	50
			(Gauge)	60	72	80	100	120	160	180	192	200
FILM DENSITY		D-1505	gm/cc	0.91								
GRAMMAGE		Internal	gm/m ²	13.7	16.4	18.2	22.7	27.3	36.4	40.9	43.7	45.5
YIELD		Internal	m ² /kg	73.1	61.1	54.9	44.0	36.6	27.5	24.4	22.9	22
			in ² /lb	51389	42953	38594	30932	25730	19332	17153	16098	15466
TREATMENT LEVEL		D-2578	dyne/cm	38								
COEFF OF FRICTION (UTR/UTR)	Dynamic	D-1894	-	0.30±0.05								
HAZE		D-1003	%	1.3	1.4	1.4	1.5	1.6	1.8	1.9	2.0	2.0
GLOSS (at 45°)		D-2457	Unit	105	105	105	105	100	100	100	100	100
TENSILE STRENGTH AT BREAK	MD*	D-882	kg/cm ²	1200								
	TD*			2500								
	MD*		(KPsi)	17.0								
	TD*			35.5								
ELONGATION AT BREAK	MD*	D-882	%	200								
	TD*			60								
LINEAR SHRINKAGE (max) (5 Minutes at 130°C)	MD*	D-1204	%	6.0								
	TD*			3.0								
WATER VAPOUR TRANSMISSION RATE (38°C & 90% RH)		F-1249	gm/m ² /day	7.0	6.8	6.5	6.0	5.7	5.0	4.7	4.5	4.5
			(gm/100 in ² /day)	0.45	0.44	0.42	0.39	0.37	0.32	0.30	0.29	0.29
OXYGEN TRANSMISSION RATE (23°C & 0% RH)		D-3985	cc/m ² /day	2000	1800	1800	1700	1600	1300	1200	1200	1200
			(cc/100 in ² /day)	129	116	116	110	103	84	77	77	77

Ref no QAD UFLI S/20 - B26/1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

STORAGE & HANDLING

FLEXOPP™ does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXOPP™ is best suitable for use within 6 months from date of dispatch.

FOOD CONTACT

FLEXOPP™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

**TDS issued on 29-06-2021. All previous version of this grade are invalid.

FlexFilms

Manufacturing Facilities at
India | UAE | Poland | Egypt | Mexico |
USA | Hungary | Russia | Nigeria
enquiry@flexfilm.com
www.flexfilm.com