


C-CPT

Transparent Twist Grade CPP Film

C-CPT is a Co-Extruded modified transparent film one side treatment for twist application.



FILM STRUCTURE

THE BIG DIFFERENTIATORS



Twistability
 Excellent twist retention.



Optimal COF
 Superior runnability at high speed m/c.



Good Stiffness
 High performance on high speed m/c with minimal wastage.



High Gloss
 High quality images.



Good Machinability
 Excellent runnability.

KEY FEATURES:

- Excellent Gloss & Stiffness
- Excellent Twistability
- Superior printability

APPLICATIONS:

- Twist Wrap
- Candy Wrap
- Confectionery conversion

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUES			
THICKNESS ± 5 %		Internal	Micron	25	28	33	35
			(Gauge)	100	112	132	140
FILM DENSITY		D-1505	gm/cc	0.91			
GRAMMAGE		Internal	gm/m ²	22.7	25.5	30	31.8
YIELD		Internal	m ² /kg	44.0	39.2	33.3	31.4
			in ² /lb	30932	27557	23409	22074
TREATMENT LEVEL		D-2578	dyne/cm	38			
COEFF OF FRICTION (UTR/UTR)	DYNAMIC	D-1894	-	0.60±0.05		0.50±0.05	
HAZE		D-1003	%	4.0	4.0	4.0	4.0
GLOSS (at 45°)		D-2457	Unit	85	82	80	75
TENSILE STRENGTH AT BREAK	MD*	D-882	kg/cm ²	550			
	TD*			210			
	MD*		(KPsi)	7.8			
	TD*			3.0			
ELONGATION AT BREAK	MD*	D-882	%	400			
	TD*			650			
WATER VAPOUR TRANSMISSION RATE (38° C & 90% RH)		F-1249	gm/m ² /day	12	11	9	8
			(gm/100 in ² /day)	0.7	0.7	0.6	0.5
OXYGEN TRANSMISSION RATE (23° C & 0% RH)		D-3985	cc/m ² /day	3750	3700	3550	3500
			(cc/100 in ² /day)	242	239	229	225

*Ref no QAD UFLI S/14 - C4/2

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

STORAGE & HANDLING

FLEXCPP™ does not require special storage conditions. It is recommended to storage below 30° C in order to avoid any deterioration of the film surface properties. It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXCPP™ is best suitable for use within 3 months from date of dispatch.

FOOD CONTACT

FLEXCPP™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

**TDS issued on 01-04-2020.All previous version of this grade are invalid.

FlexFilms

Manufacturing Facilities at
 India | UAE | Poland | Egypt | Mexico |
 USA | Hungary | Russia | Nigeria
 enquiry@flexfilm.com
 www.flexfilm.com