


B-TMQ-M

Moderate Barrier Metallized BOPP Film With Low SIT

B-TMQ-M is a low SIT metallized film having excellent metal bond strength, superior barrier properties, low SIT, high & broad hot tack.



THE BIG DIFFERENTIATORS



Moderate Oxygen & Moisture Barrier

Improves shelf life of chips/snacks & confectionary.



Superior Metal Bond & Metal Cracking Resistance

Durability & sustainability of barrier under extreme conditions. Enhanced Extrusion/ adhesive bond strengths.



Exceptional Metal Gloss

Enhanced graphics & images.



Enhanced seal functionality

Very Low SIT, Excellent broad & high hot tack, optimal hermetic seal designed to substantially improve productivity & operating efficiency at FFS m/c.



Optimal COF

Excellent runnability at high speed both during the lamination process as well as on FFS m/c.

KEY FEATURES:

- Excellent extrusion bond
- Good metal cracking resistance
- Low SIT (<85°C)
- High hot tack (>250 g/25mm)
- Broad sealing range
- Brilliant metal appearance

APPLICATIONS:

- Fruit candy
- Biscuits/cookies/crackers
- Confectionery
- Snacks

PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUES		
THICKNESS		Internal	Micron	15	18	20
			(Gauge)	60	72	80
FILM DENSITY		D-1505	gm/cc	0.91		
GRAMMAGE		Internal	gm/m ²	13.7	16.4	18.2
YIELD		Internal	m ² /kg	73.1	61.1	54.9
			in ² /lb	51389	42953	38594
TREATMENT LEVEL		D-2578	dyne/cm	36		
OPTICAL DENSITY (TOLERANCE : ±5%)		Internal	-	2.5		
TENSILE STRENGTH AT BREAK	MD*	D-882	kg/cm ²	1200		
	TD*			2500		
	MD*		(KPsi)	17.0		
	TD*			35.5		
ELONGATION AT BREAK	MD*	D-882	%	200		
	TD*			60		
LINEAR SHRINKAGE (max) (5 Minutes at 130°C)	MD*	D-1204	%	6.0		
	TD*			3.0		
HEAT SEAL INITIATION TEMPERATURE		Internal	°C	85		
HEAT SEAL STRENGTH	(Min.)	Internal	gm/25mm	400	450	450
WATER VAPOUR TRANSMISSION RATE (38°C & 90% RH)		F-1249	gm/m ² /day	0.25	0.2	0.2
			(gm/100 in ² /day)	0.016	0.013	0.013
OXYGEN TRANSMISSION RATE (23°C & 0% RH)		D-3985	cc/m ² /day	35	30	30
			(cc/100 in ² /day)	2.26	1.94	1.94

Ref no QAD UFLI S/20 – MB 1/1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

STORAGE & HANDLING

FLEXMETPROTECT™ does not require special storage conditions. It is recommended to storage below 30°C in order to avoid any deterioration of the film surface properties.

It is advisable to use the material on FIFO basis. The film should be kept at operating environment for 24 hours before processing. FLEXMETPROTECT™ is best suitable for use within 3 months from date of dispatch.

FOOD CONTACT

FLEXMETPROTECT™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

**TDS issued on 01-04-2020. All previous version of this grade are invalid.

FlexFilms

Manufacturing Facilities at
India | UAE | Poland | Egypt | Mexico |
USA | Hungary | Russia | Nigeria
enquiry@flexfilm.com
www.flexfilm.com